

G077 - NITECK
Cut Protection Nitrile



EN 388:2016
+A1:2018



4X43B

DEXTERITY



Features

- Polyethylene UHMWPE, nylon lining
- Good cut resistance
- Excellent dexterity
- Soft nitrile foam that makes the glove flexible and comfortable

Coating

Nitrile foam

Lining

UHMWPE polyethylene, nylon

Gauge

13

Colour

White-black/black

Application

Mechanical parts assembly, oil contact, plastic industry, mechanical industry, handling of metal sheets and metal components

Sizes

7 (S)	8 (M)	9 (L)	10 (XL)	11 (XXL)
----------	----------	----------	------------	-------------

Lenght

23 cm	24 cm	25 cm	26 cm	27 cm
9"	9,5"	9,9"	10,2"	10,6"



CUT RESISTANT GLOVE MADE OF NITRILE FOAM



Packaging

Code	Quantity
G077-DD00	1 dozen (1 bag containing 12 pairs)
G077-KD00	Carton containing 10 dozen (10 bags containing 12 pairs)

SAFETY TECHNICAL SPECIFICATIONS

The PPE is in compliance with essential requirements of (EU) 2016/425 regulation

STANDARD	DESCRIPTION	MINIMUM REQUIREMENT / RANGE	RESULT REACHED
EN 420:2003 + A1 2009	pH determination (palm)	3,5 < pH < 9,5	7,0
EN 420:2003 + A1 2009	pH determination (back)	3,5 < pH < 9,5	6,5
EN 420:2003 + A1 2009	pH determination (cuff)	3,5 < pH < 9,5	6,5
UNI EN 14362-1/3:2012	Carcinogenic and aromatic amines	≤ 30 ppm	< 5

STANDARD	DESCRIPTION	LEVEL					LEVEL REACHED
		1	2	3	4	5	
EN 388:2016+A1:2018	Abrasion resistance (number of frictions)	≥ 100	≥ 500	≥ 2000	≥ 8000	-	4
EN 388:2016+A1:2018	Cutting test : blade cut resistance (index)	≥ 1,2	≥ 2,5	≥ 5,0	≥ 10,0	≥ 20,0	X
EN 388:2016+A1:2018	Tear resistance (N)	≥ 10	≥ 25	≥ 50	≥ 75	-	4
EN 388:2016+A1:2018	Puncture resistance (N)	≥ 20	≥ 60	≥ 100	≥ 150	-	3
EN 388:2016+A1:2018 - EN ISO 13997	TDM : cutting resistance (N)	A	B	C	D	E	B
		≥ 2	≥ 5	≥ 10	≥ 15	≥ 22	
EN 388:2016+A1:2018 - EN 13594:2015	Impact protection	P			ABSENT		ABSENT
		Achieved			Test not executed		

If one of the marking indexes is marked with:

- letter "X" means that the test wasn't executed or not applicable;
- number "0" means that the test was executed but the minimum performance level hasn't been achieved